

Light measurements/LUX

Mesurements PCE 172 / LUXEMETRE
10th and 13th June 2005

Covering 705 S Standard (230 g/sqm) :	
Measurement without covering:	9 460 LUX
Measurement with covering 705 S optical White:	1 560 LUX
Translucence in %:	16,5 %

Covering 705 A Acoustic White (200 g/sqm) :	
Measurement without covering:	9 460 LUX
Measurement with covering 705 Acoustic optical White:	2 750 LUX
Translucence in %:	29.0 %

Covering 705 C Colours (230 g/sqm) :	
Measurement without covering:	9 460 LUX
Measurement with covering 705 C colour "Beige":	1 450 LUX
Translucence in %:	15.3 %

Covering 705 T Translucent (230 g/sqm) :	
Measurement without covering:	9 460 LUX
Measurement with covering 705 T Translucent:	5 080 LUX
Translucence in %:	53.7 %

Covering 705 A Acoustic Black (200 g/sqm) :	
Measurement without covering:	9 460 LUX
Measurement with covering 705 A Acoustic Black:	0.1 LUX
Translucence in %:	0 %